

# Vertical Burning Test - UL 94, Section 8

Customer : Smooth-On Inc.		Material: Urethane 98-290	
Microtek Job No. : 39316	Set No.: 1	ANSI : N/A	Color: WT
<b>SOLDER LIMITS</b>		Coating : N/A	
Temp/Time: N/Asec @ N/A°C		Nom. Sample Thk.: As-Measured	
		Avg. Sample Thk.: 3.568 mm	

Test Type Original	Sample No.	Sample Thk: (mm)	Afterflames		Afterglow t <sub>3</sub> (sec)	Sum of after flames (t <sub>1</sub> + t <sub>2</sub> ) (sec)	Sum of afterflame and afterglow (t <sub>2</sub> + t <sub>3</sub> ) (sec)	Did samples burn to the clamp?	Did the cotton ignite?
			t <sub>1</sub> (sec)	t <sub>2</sub> (sec)					
<b>CONDITION A:</b> 48 Hours 23 ± 2°C 50 ± 5% RH	1	3.016mm	0.0	0.0	0.0	0.0	0.0	No	No
	2	3.476mm	0.0	0.0	0.0	0.0	0.0	No	No
	3	3.996mm	0.0	0.0	0.0	0.0	0.0	No	No
	4	3.645mm	0.0	0.0	0.0	0.0	0.0	No	No
	5	3.625mm	0.0	0.0	0.0	0.0	0.0	No	No
<b>CONDITION B:</b> 168 Hours 70 ± 1°C	6	3.004mm	0.0	0.0	0.0	0.0	0.0	No	No
	7	3.293mm	0.0	0.0	0.0	0.0	0.0	No	No
	8	3.671mm	0.0	0.0	0.0	0.0	0.0	No	No
	9	4.073mm	0.0	0.0	0.0	0.0	0.0	No	No
	10	3.879mm	0.0	0.0	0.0	0.0	0.0	No	No

**Test Results:** Meets the requirements of UL 94 Section 8 classification V-0

Criteria Conditions	Material Classifications			Test Results	
	V-0	V-1	V-2	Cond A	Cond B
Afterflame time for individual sample t <sub>1</sub> or t <sub>2</sub>	≤10s	≤30s	≤30s	0.0s	0.0s
Total afterflame time for any condition set ( t <sub>1</sub> plus t <sub>2</sub> for the five specimens)	≤50s	≤250s	≤250s	0.0s	0.0s
Afterflame plus afterglow time for each individual specimen after the second flame application ( t <sub>2</sub> + t <sub>3</sub> )	≤30s	≤60s	≤60s	0.0s	0.0s
Afterflame or afterglow of any specimen up to the holding clamp	No	No	No	No	No
Cotton indicator ignited by flaming particles or drops	No	No	Yes	No	No



1435 Altec Street • Anaheim, CA 92805  
Tel: 1-714-999-1616 • Fax: 1-714-999-1636  
www.thetestlab.com

## CERTIFICATE OF CONFORMANCE

Microtek Laboratories certifies that the test equipment used complies with the calibration requirements of ANSI/NCSL Z540-1, IPC-QL-653, and ISO/IEC-17025 and that the data contained in this report is accurate within the tolerance limitation of this equipment.

The materials and/or devices furnished on this order have been tested/analyzed/and inspected in accordance with all designated instructions and specifications. Physical reports and supporting records are on file and available for inspection at Microtek Laboratories for a period not less than five years. Tested samples will be stored at Microtek Laboratories for a period not less than two years unless the customer requests the release of the test samples.

All test procedures detailed are complete. If any additional information or clarification of this report is required, please contact us.

Thank you for selecting Microtek Laboratories for your testing requirements.

Report prepared by,

A handwritten signature in black ink, appearing to read 'Josephin Mazariegos', written in a cursive style.

Josephin Mazariegos  
Administrative Assistant  
MICROTEK LABORATORIES  
Date: 2010-06-09

Respectfully submitted,

A handwritten signature in black ink, appearing to read 'Russ Shepherd', written in a cursive style.

Russ Shepherd  
Director PCB/PWB Test Programs  
MICROTEK LABORATORIES  
Date: 2010-06-09